

Product Specifications



Product	Product #	Sheen	Product Use	Vol Solids +/- .1%	Wt./Gal.	Hrs. Dry Re-Coat ¹	VOC g/L	Coverage ² Per Gal.
Waterlox Original Sealer/Finish	TB 5284	Medium	Sealer & Finish	22.3	6.95	24	614	500 Sq. Ft.
Waterlox Original 350 VOC Sealer/Finish	TB 6038	Medium	Sealer & Finish	27.8	9.35	24	347	500 Sq. Ft.
Waterlox Original Satin Finish	TB 6044	Satin	Finish	33.6	7.28	24	524	500 Sq. Ft.
Waterlox Original 350 VOC Satin Finish	TB 6035	Satin	Finish	34.3	9.10	24	345	500 Sq. Ft.
Waterlox Original 450 VOC Satin Finish	TB 6045	Satin	Finish	36.1	8.25	24	445	500 Sq. Ft.
Waterlox Original High Gloss Finish	TB 3182	High Gloss	Finish	34.1	7.18	24	523	500 Sq. Ft.
Waterlox TrueTone Color-Infused Tung Oil Stains	Various	Matte/Flat	Sealer/Stain	70-75	7.58-8.77	24	< 275	3,200-3,400 Sq. Ft.
Waterlox TrueTone Buff-In Tung Oil Finish	TB 7011	Matte/Flat	Finish	75.0	7.58	24	< 275	3,200-3,400 Sq. Ft.
Waterlox Marine Sealer	TB 3809	Medium	Exterior Primer	22.3	6.95	24	614	500 Sq. Ft.
Waterlox Marine Satin Finish	TB 6032	Satin	Exterior Finish	36.0	7.27	24	508	500 Sq. Ft.
Waterlox Marine High Gloss Finish	TB 3940	High Gloss	Exterior Finish	43.6	7.44	24	450	500 Sq. Ft.
Urethane Satin XL-89	TB 5930	Satin	Finish	36.4	7.35	6 ³	527	450 Sq. Ft.
Urethane Gloss XL-88	TB 4252	Gloss	Finish	34.0	7.22	6 ³	547	450 Sq. Ft.
Waterlox Pure Tung Oil	TB 6050	Matte	Sealer & Finish	100.0	7.8	24+	0	4,000 Sq. Ft.

¹ Based on adequate cross-ventilation, 70° F; and < 50% relative humidity. Review the Ventilation FAQs on our website at waterlox.com. ² Suggested spread rate(s). ³ After 12 hours must be sanded for inter-coat adhesion.